

König et al. Reply: In a recent Letter [1] we developed a theory of carrier-induced ferromagnetism in diluted magnetic semiconductors. We analyzed the elementary spin excitations at low temperatures, where spin waves can be approximated as non-interacting Bose particles (“independent spin-wave theory”). In addition, we proposed a simple ad hoc “self-consistent spin-wave” approximation for higher temperatures in order to demonstrate the increasing inadequacy of mean-field theory critical temperature estimates at high carrier densities.

Following Ref. [2], Yang *et al.* [3] use an equation-of-motion approach under the Tyablikov decoupling scheme to arrive at an alternative “self-consistent spin-wave” theory. As we will show now, it is straightforward to rederive this scheme within our formulation, and thereby provide a clearer physical picture of the nature of their approximation.

The independent spin-wave theory describes small amplitude collective fluctuations of the magnetization, spin waves with dispersion Ω_p . It predicts for the thermal average of the impurity-spin density

$$\langle S^z \rangle = \frac{1}{V} \sum_{|\vec{p}| < p_c} \{ S - n(\Omega_p) \}. \quad (1)$$

The Bose function $n(x)$ reflects the fact that the spin waves are approximated by independent Bose particles. It is known [4] that this equation yields the correct prefactor of the characteristic $T^{3/2}$ -law.

A self-consistent spin-wave theory provides an approximate theory of large amplitude magnetization fluctuations, taking into account, for example, spin-quantization constraints on boson occupation numbers.

Weiss mean-field theory, which is expected to be accurate for a model with static long-range interactions, neglects correlation and, hence, spin-wave dispersion, but treats the problem self consistently. Then the constraint on the number of spin waves per impurity spin ($\leq 2S$) leads to $\langle S^z \rangle = cSB_S(\beta S\Omega)$ or, equivalently,

$$\langle S^z \rangle = c \{ S - n(\Omega) + (2S + 1)n[(2S + 1)\Omega] \} \quad (2)$$

where $B_S(x)$ is the Brillouin function, and Ω denotes the energy of an uncorrelated spin flip, which is independent of momentum $\vec{p}$. The mean-field theory is closed by specifying the dependence of Ω on $\langle S^z \rangle$ (it is $\Omega = J_{pd}n^*$ where n^* is the free-carrier spin density). The second Bose function in Eq. (2) is the correction term from spin kinematics and rules out unphysical states. Due to the neglect of correlation, Weiss mean-field theory can substantially overestimate the critical temperature [5]. It fails to describe the low-temperature magnetization as well.

A self-consistent spin-wave scheme ideally (i) reduces to the independent spin-wave theory at low temperatures, (ii) simplifies to Eq. (2) in the Ising limit, $\Omega_p \rightarrow \Omega$,

and (iii) yields a second-order phase transition by allowing for the trivial solution $\langle S^z \rangle = 0$.

At low temperatures the correction term in Eq. (2) is negligible and Eq. (2) reduces to Eq. (1) if Ω is replaced by an effective energy which accounts for the spin-wave dispersion Ω_p ,

$$n(\Omega) \equiv \frac{1}{cV} \sum_{|\vec{p}| < p_c} n(\Omega_p) \quad (3)$$

(= Φ in the notation of Ref. [3]). In Ref. [1] we obtained a self-consistent spin-wave scheme by using the replacement $\Omega \rightarrow \Omega_p$ in Eq. (2) and averaging over momenta, $(1/cV) \sum_{|\vec{p}| < p_c} \dots$. This is equivalent to restrict the number of spin waves *per wave vector* $\vec{p}$ and turns out to be too restrictive at low temperatures, as we pointed out in Ref. [1]. Nevertheless, requirements (ii) and (iii) are still satisfied and the prefactor of the $T^{3/2}$ -law is only slightly changed. This approximation would completely fail in reduced-dimension systems as emphasized in Ref. [3] but these are not of interest here [6].

Equation (3) of Ref. [3] is identical to Eq. (2) with Ω determined by Eq. (3). Now all the requirements (i), (ii), and (iii) are satisfied. The scheme proposed by Yang *et al.* is, therefore, equivalent to Weiss mean-field theory but with an effective (constant) spin-flip energy Ω which accounts for correlation.

Finally, we note that in both self-consistent schemes, the one in Ref. [1] and the one proposed in Ref. [3], not only does the magnetization of the impurity spins vanish at the critical temperature but, by construction, the polarization of the free carriers goes to zero as well. This is not generally the correct physical picture. For example, in the limit of low carrier densities, the local band polarization of the free carriers remains finite even above T_c [5] and neither scheme gives reliable T_c estimates.

-
- [1] J. König, H.H. Lin, and A.H. MacDonald, Phys. Rev. Lett. **84**, 5628 (2000).
 - [2] H.B. Callen, Phys. Rev. **130**, 890 (1963).
 - [3] M.F. Yang, S.J. Sun, and M.C. Chang, preceding comment, Phys. Rev. Lett., cond-mat/0008098.
 - [4] F.J. Dyson, Phys. Rev. **102**, 1230 (1956).
 - [5] J. Schliemann, J. König, H.H. Lin, and A.H. MacDonald, preprint.
 - [6] Ferromagnetic semiconductors have a very large easy axis magnetic anisotropy in quantum wells [B.H. Lee, T. Jungwirth, and A.H. MacDonald, Phys. Rev. B **61**, 15606 (2000)].